

Data sheet and application

DIM L-30 ©

DIM L-30 6-GZ-60-S

Characteristics

Cutting stability, tough, impact resistant,

High resistance to wear in case of glas and carbon fibre reinforced plastic syringes.

Hardenable, polishable, chrome platable.

54-60 HRC

Fields of application

cutting-wearing edge

Cold-heat working tools

1.1730/C45 (hardened)

1.2379 / 1.2363

1.2080 / 1.2162

1.2764

1.2842 / 1.2510

1.7131

K 190 / K 340

ELMAX

SVERKER

SKD1/12/62

SKS3

Chemical composition

С	Si	Mn	Cr	Fe
0,5	3,0	0,5	9,5	Rest