

DIM L-70 / Al Mg3[©]

DIM L-70 Mg3
3.3536 / AlMg3

Characteristics

Well circulating,
seawater resistant,
Must be applied, if later anodised (here, no silicon alloy application).
Elongation 20%,
Tensile strength Rm N/mm²: 200

Fields of application

If anodised later:
Alu-components
Alu-castings
Metal sheets
Al-Mg-alloys among themselves
EN AW-6060 (AlMgSi0,5)