

Data sheet and application

DIM L-70 / Al Mg4,5MnZr ©

DIM L-70 Al Mg4,5MnZr
3.3546 / AlMg4,5MnZr

Characteristics

Unsusceptible to hot-shortness,
seawater resistance,
Elongation 20%,
Tensile strength Rm N/mm²: 300

Fields of application

Al-Mg Alloys
Joint Welding